

# Technical Data Sheet Type ACMP

# **CELLCOM - AZO/ST**

Cas No. 123-77-3

EC No. 204-650-8

UN No. 3242

# N=N

MW 116.08

#### **Azodicarbonamide**

Item	Specification
Appearance	Orange yellow fine powder
Decom. Temp.	201 - 205°C
Gas Volume(in Air)	270 - 290ml/g
Part. Sz.(by Malvern)	20 - 24μm
Moisture	Max. 0.3%
pH	6.5 - 7.5



< CELLCOM - AZO/ST >

### Description

Azodicarbonamide (AC or ADCA) is the most popular chemical blowing agent. Generally, AC is orange to pale yellow, crystalline solid with a decomposition temperature in air of 201~205 °C. Unlike a number of other chemical blowing agent, AC is self-extinguishing when flame is removed. The decomposition residues are odorless, non-toxic, non-coloring and non-straining. The particle size and distribution can be controlled with widely different ranges. The particle size and distribution is one of the

#### Application

significant factors.

X-linX-linked Polyolefinked Polyolefin

#### Advantages

This foaming agent has free of agglomeration between particles and excellent free flowing property .

#### Transport&Storage Precautions

Expiration Date: 1 year

Storage Instruction : Keep container tightly closed in a dry and well-ventilated place.

Transport : Avoid contact with a direct ray of light and moisture.

Using : Wear protective gloves, dust mask and goggles.

Disposal : Contact a licensed professional waste disposal service to

dispose of this material.

Fire & Explosive : Non flammable, Non explosive. Decompose around

200°C

Extinguish Media : Use water spray, alcohol-resistant foam, dry chemical

or carbon dioxide.

## Packaging

25kg Carton Box / 25kg Bag

#### KUM YANG COMPANY LIMITED

HEAD OFFICE & FACTORY 81, NAKDONG-DAERO 960 BEON-GIL, SASANG-GU, BUSAN, KOREA (617-805)

TEL: 82-51-316-5881/7 FAX: 82-51-325-5887 www.kyc.co.kr SEOUL OFFICE ROOM NO.1201, TRADE TOWER, 511, YEONGDONG-DAERO, GANGNAM-GU, SEOUL, KOREA (135-729) TEL: 82-2-3454-1751

FAX: 82-2-3143-0641/0642

Rev1. Revision Date : 2018. 02. 23

개정 내용

1. SPEC 재확인 및 운송&저장 관련 내용 SDS 와 동일하게 변경(2018.02.23)

작성자 : 이재일

승인자 : 백대완